

Press Ceramic Casting Curve

① Press Ceramic Casting Temperature and Program Settings

Embedding circle	Initial temperature	Heating rate	Holding temperature	Residence time	Cooling
100g	700°C	60°C/min	910°C	20min	Natural cooling

